



ACRIFIX®
Adhesive

ACRIFIX® 1S 0126

1-Component Solvent Adhesive

Product and Use

Type of Adhesive

1-Component solvent adhesive.
Low viscosity, transparent clear, slightly purple to slightly yellow, physically curing.

Application

For making T-bonds and bonding narrow areas of all kinds of uncrosslinked PLEXIGLAS®, preferentially for crack-free bonding also of lightly internally stressed parts, e.g. those made of extruded PLEXIGLAS® XT and injection moldings made from PLEXIGLAS® molding compound. Cracking only occurs in parts with extreme internal stresses.

ACRIFIX® 1S 0126 is only gap-filling to a certain extent. The bond is firm within a short time. Rapid further treatment possible. High ultimate strength. For other materials, conduct prior tests.

For commercial use only.

Storage/Transport

Keep container firmly closed, store in a cool place.
UN 1993

Working Instructions

Normally, a sawn or milled edge of one article is bonded at right angles to the original surface of another. The parts to be bonded must have a very accurate fit. Grooves and notches are only partially filled. Clean the adherents with petroleum ether or isopropyl alcohol before applying the adhesive.

ACRIFIX® 1S 0126 is applied from a nozzled bottle to the edge of one of the items to be bonded, which, starting from one side, is then placed in contact with the second. After a short holding time, the bond is locked in position.

When bonding sawn edges, bubble formation can be reduced by smoothing the edges prior to bonding, either with a scraper or with fine, wet abrasive paper, grit 400 to 600 (if possible at right angles to the sheet edge), or by milling or diamond cutting.

More Information

If the product is stored in PE application bottles, it must be ensured that the adhesive is always fresh, as its composition changes by evaporation of predominantly one component and solvation is impaired.

Whitening around the adhesive joint is due to water condensing from the air (especially if the room temperature is low).

Attention: When pre-bonding with ACRIFIX® 1S 0126, curing of ACRIFIX® 2R adhesives can be impaired. ACRIFIX® 1S 0126 can turn yellow as a result of exposure to light; however, the yellowing has no effect on the adhesion. To adjust the viscosity, ACRIFIX® 1S 0126 can be mixed with ACRIFIX® 1S 0127 in any ratio.

For further details, please see our Guideline, "Joining Ref. No.: 311-3"



Properties of Bonds

Initial bond

PLEXIGLAS® GS / PLEXIGLAS® GS: ~ 30 sec.
PLEXIGLAS® XT / PLEXIGLAS® XT: ~ 10 sec.

Subsequent treatment of bonded items

Not within the first three hours

Strenght of Bonds

The bonds only acquire their final strength after about 24 hours or after immediate annealing as soon as the adhesive has cured.

Tensile shear strength (v = 5 mm/min)

Material (with itself)	Non annealed	annealed (5 h at 80°C)
PLEXIGLAS® GS OFOO	15 – 25 MPa	25 – 35 MPa
PLEXIGLAS® XT OAOOO	15 – 25 MPa	25 – 35 MPa

Annealing increases the strength and also improves the weather resistance.

Appearance

- Colorless clear.
- Rather more bubbles with PLEXIGLAS® XT and fewer with PLEXIGLAS® GS.
- Bleeding may occur with colored grades.

Limitation of Liability

Our ACRIFIX® adhesives and other service products were developed exclusively for use with our PLEXIGLAS® products and are specially adjusted to the properties of these materials. Any recommendations and guidelines for workshop practice therefore refer exclusively to these products.

Claims for damages, especially under product liability laws, are ruled out if made in connection with the use of products from other manufacturers.

Safety Measures and Health Protection

For further information on safety measures, the exclusion of health risks when handling adhesives and on their disposal, see our Safety Data Sheet.

Availability according to the current sales range.



Typical Values	
Properties	Values
Viscosity; Brookfield II/6/20°C	850 – 1100 mPa • s
Density (20 °C)	~ 1.14 g/cm ³
Refractive index n_{D20}	~ 1.42
Color	transparent clear, slightly purple to slightly yellow
Flash point; DIN EN ISO 13736	≥ 24°C
Solids content	approx. 10 %
Storage stability	2 years after filling if correctly stored
Storage temperature	max. 30°C
Packaging materials	Colored glass and aluminum
Thinner	ACRIFIX® 1S 0126 can be thinned with ACRIFIX® 1S 0127 at any ratio
Curing	Physically, through evaporation and absorption in the bonded articles.
Cleaning agents for equipment	Ethyl acetate

POLYVANTIS GmbH

Riedbahnstraße 70
64331 Weiterstadt
Germany

www.plexiglas.de
www.polyvantis.com

® = registered trademark

Semi-finished polymethyl methacrylate (PMMA) products from POLYVANTIS are sold on the European, Asian, African and Australian continents under the registered trademark PLEXIGLAS®, in the Americas under the registered trademark ACRYLITE®, both owned by Röhm GmbH, Darmstadt, or its affiliates. Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments.

The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.