

INDUSTRIAL -

 Issue date : 27/06/2014
 Date last modification : 22/01/2020

4-IL3B-08279 RI-1110/145 PVC MATT BLACK AP906 WKPE140
Face Material

Matt black embossed polymeric vinyl.

Type	Embossed polymeric vinyl	
Colour and Finish	Matt black	
Weight	194 g/m ² ±10%	ISO-536
Thickness	145 μ ±10%	ISO 534-80

Adhesive

Solvent based permanent acrylic adhesive featuring good water and cleaning agents resistance. High adhesion on a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	AP 906
Type	Acrylic permanent
Min. Appl. Temp.	+10°C
Service Temp.	-40 / + 140
Shear	Very high
Tack	High N/inch ²
Final Adhesion	14 N/inch

Liner

Type	Siliconised two side PE Kraft	
Colour and Finish	White	
Weight	140 g/m ² ±10%	PP-032 - ISO 536
Thickness	150 μ ±10%	ISO 534
Transparency	n.a. %	DIN 53 147-64

Applications

For decoration and lining in the Automotive industry. It can be used as blackboard vinyl for an easy to write and easy to erase surface for a very long time.

Flammability: Self-exstinguish (ISO-3795)

Outdoor Durability: UP TO 5 YEARS.

The durability data re given for unprinted film only and for vertical exposure, zone I (Italy, North-Est Europe)

Printing Methods

As a rule it is not printed.

Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.


Ritrama S.p.A.

 Via Senatore Simonetta, 24
 20867 Caponago (MB) ITALY
 e-mail: info@ritrama.com
 www.ritrama.com
