### TECHNICAL DATA SHEET

**RITRAMA** 

ISSUE:1 DATE:13/08/2021

### Ri-Jet Decobus M85 Rem SB

PRODUCT
DESCRIPTION /
BENEFITS

Ri-Jet Decobus M85 Rem SB series is a self-adhesive film for Large Format Digital printing, especially designed for public transport advertising.

The high opacity (HOP) monomeric vinyl, UV stabilised, has an external colour stability up to 3 years, specially developed to be printed with solvent, eco-solvent, latex, and UV inkjet printing presses. The removable solvent-based adhesive provides an easy and clean removability from public transport vehicles. The 135 g/m² liner or the 140g/m² micro-embossed PE coated kraft paper ensures good planarity and printing results. All our products are REACH & RoHS compliant.

### **TYPICAL USE**

Short term outdoor advertising: trains, trams, bus, taxi

#### CONSTRUCTION

- Face film: 85 µm calendered monomeric film
- Adhesive: removable solvent-based acrylic
- Release liner: clay coated kraft paper 135 g/m<sup>2</sup>

Airflow liner: micro-embossed PE coated kraft paper 140 g/m<sup>2</sup>

### **Products:**

White Satin finish: Code 09366 - Ri-Jet Decobus M85 White Satin HOP Rem SB

03845 - **Ri-Jet Decobus M85 White Satin HOP Rem SB Airflow** 08880 - **Ri-Jet Decobus M85 White Satin HOP Rem SB PE** 

### **CONVERTING METHOD**

Specially developed to be printed with solvent, eco-solvent, latex, and UV inkjet printing presses. To achieve the best possible print quality, make sure that the correct ICC profiles or printer settings are used. The printed media should dry minimum 24h prior to lamination. We recommend a lamination with Ri-Lam M70 Clear Gloss, Matt or Satin to protect the printed image from UV fading and mechanical abrasion.

# APPLICATION METHOD / INSTRUCTIONS FOR USE

Dry and wet application method on clean and degreased substrates for the product with kraft liner, while only the dry application method will be used with the Airflow liner. Application temperature above 10°C.

## EXPECTED DURABILITY

The expected vertical outdoor durability in Central Europe (zone 1) is 3 years.

This information is based on real file experience and artificial aging according to ISO 4892-2.

Note: Exposure to severe temperature and ultra-violet light will cause a quicker deterioration. This applies also to polluted area, high altitude, horizontal applications, and south-facing exposure in north hemisphere.

### **SHELF LIFE**

Shelf life is 2 years, when stored at 23  $^{\circ}$ C and 50  $^{\circ}$ C relative humidity conditions. Higher temperatures and/or humidity levels will reduce product shelf life. NB: Printing results start to deteriorate after 12 months storage.



ISSUE: 1 DATE: 13/08/2021

## Ri-Jet Decobus M85 Rem SB

PHYSICO-CHEMICAL PROPERTIES / TYPICAL VALUES

85 µm	ISO 534-80
105 µm	ISO 534-80
> 25 N/cm	ISO 527
>100%	ISO 527
Self-extinguishing	ISO 3795:1989
0,5 mm	FTM 14
5 N/25mm	FTM1
6 N/25mm	FTM1
7 N/25mm	FTM1
+10 °C	
From -40 °C to +90 °C	
135 g/m <sup>2</sup>	ISO 536
140 g/m2	
No effect	200 hours exposure
No effect	24 hours immersion
No effect	24 hours immersion
No effect	10 minutes immersion
	> 25 N/cm >100% Self-extinguishing 0,5 mm  5 N/25mm 6 N/25mm 7 N/25mm +10 °C From-40 °C to +90 °C 135 g/m² 140 g/m2 No effect No effect No effect

QUALITY CERTIFICATION



### **DISCLAIMER**

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

